PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

A34

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : A61K 38/24, 38/04, 9/14, 9/52

A1

(11) International Publication Number: WO 00/40259

(43) International Publication Date: 13 July 2000 (13.07.00)

(21) International Application Number: PCT/KR99/00071

(22) International Filing Date: 11 February 1999 (11.02.99)

(30) Priority Data:
1998/62142 30 December 1998 (30.12.98) KR

(71) Applicant *(for all designated States except US)*: DONG KOOK PHARMACEUTICAL CO., LTD. [KR/KR]; 997–8, Taechi–dong, Kangnam–ku, Seoul (KR).

(72) Inventors; and

(75) Inventors/Applicants *(for US only)*: BAEK, Myoung, Ki [KR/KR]; 302, 294–3, Sukchon–dong, Songpa–ku, Seoul (KR). PARK, Jin, Kyu [KR/KR]; 4–206, Hanyang Apt., 54, Myoungil–dong, Kangdong–ku, Seoul (KR). PARK, Mork, Soon [KR/KR]; 105–902, Youngjinroyal Apt., Joongli–dong, Taeduck–ku, Taejon (KR). PARK, Tae, Kwan [KR/KR]; 211–1501, Expo Apt., Chunmin–dong, Yusung–ku, Taejon (KR). CHOI, Seung, Ho [KR/KR]; 301, Sangrok Villa, 524–3, Deungchon 2–dong, Kangseo–ku, Seoul (KR).

(74) Agents: HWANG, E–Nam et al.; Yegun Building, 3rd floor, 823–42, Yoksam–dong, Kangnam–ku, Seoul 135–080 (KR).

(81) Designated States: BR, CA, CN, IN, JP, MX, TR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published
With international search report.

(54) Title: PROLONGED RELEASE MICROSPHERE ENCAPSULATING LUTEINIZING HORMONE–RELEASING HORMONE ANALOGUES AND METHOD FOR PREPARING THE SAME

(57) Abstract

There is disclosed a prolonged release microsphere which can constantly release medicinal drugs, such as luteinizing hormone–releasing hormone analogues and encapsulate them at high content rates. It is prepared by dissolving a copolymer of lactide and gycolide in methylene chloride, dissolving a luteinizing hormone–releasing hormone analogue and a release–controlling material in a subsidiary solvent, combining the above two solutions with each other to produce an emulsion phase, dispersing the emulsion phase in a solution of polyvinyl alcohol in distilled water to give a single emulsion system, removing the combined solvent of the emulsion phase to generate a polymeric microsphere; freeze–drying the polymeric microsphere. The microsphere prepared has a much finer inner structure, by virtue of which the microsphere is secured in a constant release rate. The single emulsion system which simplifies the preparation, allows for the maintenance of a drug content of 10 % or more. The charged groups of the release–controlling materials associated with the polymers minimize the excess release of the oppositely charged drugs at an initial stage, playing an important role in keeping the release rate constant.

PROLONGED RELEASE MICROSPHERE ENCAPSULATING LUTEINIZING HORMONE-RELEASING HORMONE ANALOGUES AND METHOD FOR PREPARING THE SAME

Technical Field

The present invention relates to a microsphere encapsulating luteinizing hormone-releasing hormone (hereinafter referred to as "LHRH") analogues, which is able to constantly release them for a long period of time. Also, the present invention is concerned with a method for preparing such a prolonged release microsphere.

Background Art

Physiologically, when testosterone or estrogen is in a low concentration level in blood or when hypothalamic-releasing hormone is stimulated, gonadotropin-releasing hormone (hereinafter referred to as "GnRH") is secreted from the hypothalamus. The GnRH is then transferred through the hypothalamic-pituitary portal system to the pituitary gland at which the GnRH stimulates the synthesis and secretion of luteinizing hormone (hereinafter referred to as "LH") and follicle stimulating hormone. As a result, testosterone or estrogen is secreted.

LHRH analogues act on the pituitary gland to inhibit the secretion of LH, thus resulting in the antagonizing of the liberation of testosterone and estrogen into the bloodstream. By taking advantage of this antagonistic action, the diseases caused by testosterone and estrogen, such as prostatic cancer, breast cancer, endometriosis and the like, have recently been therapeutically treated.

Like general peptide drugs, LHRH is, however, very instable within the gastro-intestinal tract and shows a low uptake efficiency therein. Therefore, the administration of LHRH has been usually performed via injection. The administration via injection also has a significant disadvantage of being very poor in bioavailibility so that LHRH is required to be injected daily. Such injection administration also requires a long cure period, which causes a problem in a patient's adaptation to the drug, therapeutic efficiency, and treatment.

Extensive research has been made on the use of poly(lactide-co-

Disclosure of the Invention

The intensive and thorough research on a prolonged release microsphere, repeated by the inventors aiming to release peptide drugs continuously for an extended period of time, resulted in the finding that, when an appropriate combination of two poly(lactide-co-glycolide) copolymers, which have an equimolar ratio between their lactide moiety and glycolide moiety and have a carboxyl group and a dodecyl group at their ends, is used as a carrier for drug, the microsphere is enhanced in biodegradation rate as well as in drug content. The negative charge of the carboxyl group attached to the end of the biodegradable polymer form an ion bond with the positive charges that the peptide drugs possess, increasing the drug content in the microsphere and preventing the drugs from being released excessively at an initial time due to diffusion. The dodecyl group plays an important role in controlling the degradation rate of the microsphere. Consequently, the microspheres in the body release LHRH analogues continuously to maintain the concentration of testosterone and estrogen in blood for an extended period of time, so as to improve the therapeutic efficiency of and the patient's adaptation to the drugs.

Therefore, it is an object of the present invention to provide a prolonged release microsphere which can control the release of drugs for a sustained period of time.

It is another object of the present invention to provide a prolonged release microsphere which is high in the content of therapeutically effective ingredients.

It is a further object of the present invention to provide a method for preparing such a prolonged release microsphere with ease and a good efficiency.

In accordance with an aspect of the present invention, there is provided a prolonged released microsphere, which is composed of a poly(lactide-co-glycolide) copolymer and encapsulate a luteinizing hormone-releasing hormone analogue.

In accordance with another aspect of the present invention, there is provided a method for preparing a prolonged release microsphere, comprising the steps of: dissolving a copolymer of lactide and glycolide in methylene chloride; dissolving a luteinizing hormone-releasing

controlled in a double manner by the actions of the functional groups, i.e. carboxyl group and dodecyl group, attached to the ends of the two polymers which compose the microsphere. The carboxyl group forms a hydrophobic ion pair with LHRH analogues, so the release rate thereof is retarded. The dodecyl group inhibits the enzymatic action to degrade the microsphere, so the integrity of the biodegradable microsphere is sustained. Therefore, the drug contained in the microsphere is bot released in a sudden burst.

The compound suitable to retard the release rate of LHRH analogues must form the hydrophobic ion pair with LHRH analogues as well as can be dissolved in the organic solvent. Preferable examples to meet these standards include sodium oleate, deoxycholic acid, cholic acid, fatty acids and phosphatidic acids.

The biodegradable microsphere of the present invention is aporous with an ultrafine inner structure, as shown in Figs. 1 and 2. The data obtained from an *in vitro* release test demonstrate that LHRH is released at relatively constant rates from the microspheres of the invention, as shown in Fig. 3. The microspheres were measured for their weight loss in order to obtain the information about their biodegradation rates, which finally told that the microspheres are completely decomposed on around the 45th day after testing, as shown in Fig. 4. The data obtained from an *in vivo* release test, shown in Fig. 5, are well correlated with those of Fig. 4.

A better understanding of the present invention may be obtained in light of the following examples which are set forth to illustrate, but are not to be construed to limit the present invention.

EXAMPLE I : Preparation of Biodegradable Microsphere Containing Leuprorelin acetate

A microsphere was made from biodegradable PLGA in an O/W (oil in water) mono-emulsification method.

In 3 ml of methylene chloride was dissolved 350 mg of each of a PLGA which has a dodecyl group at its end and a molecular weight of 12,000 with 50:50 lactide moiety:glycolide moiety, such as that sold by Boehringer Ingelheim under the brand name of RH502, and a PLGA which has a carboxyl group at its end and a molecular weight of 8,600

EXAMPLE IV: Preparation of Biodegradable Microsphere Containing Leuprorelin Acetate using Homogenizer

In 5 ml of methylene chloride were dissolved 200 mg of each of RG502H and RG502. This methylene chloride solution was sufficiently mixed with a solution of 50 mg of leuprorelin acetate in 1 ml of N-methyl-2-pyrrolidone. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.5 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a homogenizer at 700 rpm for 30 min. Thereafter, microspheres were prepared by following the remaining procedure of Example I.

EXAMPLE V: Preparation of Biodegradable Microsphere Containing Leuprorelin acetate with Sodium Oleate

In 1 ml of methylene chloride were dissolved 200 mg of each of RG502H and RG502. This methylene chloride solution was sufficiently mixed with a solution of 50 mg of leuprorelin acetate and 3.105 mg of sodium oleate in 1 ml of N-methyl-2-pyrrolidone. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.3 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a homogenizer at 700 rpm for 30 min. Thereafter, microspheres were prepared by following the remaining procedure of Example I.

EXAMPLE VI: Preparation of Biodegradable Microsphere Containing Sodium Oleate/Leuprorelin Complex

17.5 mg of sodium oleate and 50 mg of leuprorelin acetate were reacted in distilled water to yield precipitates which were, then, collected and freeze-dried. They were dissolved in a mixed solution of 0.66 ml of N-methyl-2-pyrrolidone and 1.33 ml of methylene chloride which contained 200 mg of each of RG502H and RG502. To the saturated solution with the polymer and the drug, 250 ml of a solution of 0.3 wt% polyvinyl alcohol in distilled water containing 2 g of methylene chloride was added and, then, emulsified by using a homogenizer at 700 rpm for 30 min. Thereafter, microspheres were prepared by following the

TEST EXAMPLE III: *in vivo* Drug Release of Microspheres

The biodegradable microspheres prepared in Examples were tested for in vitro release as follows. The microspheres were introduced into the femoral regions of rats via intramuscular injection and the remaining microspheres were taken from the femoral regions by incising the regions every fifth day. The microspheres taken were homogenized in 10 ml of a solution of 0.02 wt% Tween 80 (polyoxyethylene 20 oleate, Junsei Chemical Co.) in a 0.333 M phosphate buffer (pH 7.0). After further addition of 10 ml of the buffer and 10 ml of methylene chloride, the drugs were extracted in an aqueous layer. These extracts were quantified by HPLC under the same condition as that of the *in vitro* release test and the results are shown in Fig. 5.

Brief Description of the Drawings

Fig. 1 is an SEM photograph showing the microsphere of the present invention;

Fig. 2 is an SEM photograph showing a cross section of the microsphere of the present invention.

Fig. 3 is a plot showing the *in vitro* release rates of the microspheres against time.

Fig. 4 is a plot showing the weight loss rates of the microspheres against time.

Fig. 5 is a plot showing the *in vivo* release rates of the microspheres against time.

Industrial Applicability

As described hereinbefore, the microspheres prepared according to the present invention have much finer inner structures than do conventional microspheres, by virtue of which the microspheres are secure in a constant release rate. The single emulsion system of the present invention simplifies the preparation process of the microsphere, enabling it to maintain a drug content of 10% or more. In addition, the charged groups of the release-controlling materials associated with the polymers minimize the excess release of the oppositely charged drugs at

CLAIMS

1. A prolonged released microsphere, which is composed of a poly(lactide-co-glycolide) copolymer and encapsulate a luteinizing hormone-releasing hormone analogue.

2. A prolonged released microsphere as set forth in claim 1, wherein the luteinizing hormone-releasing hormone analogue is selected from the groups consisting of goserelin acetate, nafarelin acetate, buserelin acetate and leuprorelin acetate.

3. A prolonged released microsphere as set forth in claim 1, wherein the copolymer consists of a polylactide and a polyglycolide either of which have a dodecyl group and a carboxyl group at their ends.

4. A method for preparing a prolonged release microsphere, comprising the steps of:

dissolving a copolymer of lactide and glycolide in methylene chloride;

dissolving a luteinizing hormone-releasing hormone analogue and a release-controlling material in a subsidiary solvent;

combining the above two solutions with each other to produce an emulsion phase;

dispersing the emulsion phase in a solution of polyvinyl alcohol in distilled water to give a single emulsion system;

removing the combined solvent of the emulsion phase to generate a polymeric microsphere;

freeze-drying the polymeric microsphere.

5. A method as set forth in claim 4, wherein the single emulsion system comprises 75.0-99.0 wt% of an aqueous phase and 0.3-0.5 wt% of polyvinyl alcohol and the emulsion phase comprises 0.50-10.0 wt% of methylene chloride and 0.2-10.0 wt% of the subsidiary solvent.

6. A method as set forth in claim 4 or 5, wherein the subsidiary solvent is N-methyl-2-pyrrolidine.

FIG. 1



FIG.3


100
80
60
40
20
0
LHRH Release (%)
0
5
10
15
20
25
30
Time (days)
: EXAMPLE 1
: EXAMPLE 2
: EXAMPLE 3
: EXAMPLE 4
: EXAMPLE 5
: EXAMPLE 6

FIG.5


100
80
60
40
20
0
LHRH Release (%)
0
5
10
15
20
25
30
Time (days)
-●- : EXAMPLE 1
-■- : EXAMPLE 2
-▲- : EXAMPLE 3
-▼- : EXAMPLE 4
-◆- : EXAMPLE 5
-⬢- : EXAMPLE 6

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.
PCT/KR 99/00071

In Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
EP A1 505966	30-09-1992	AT E 124254	15-07-1995
		AU A1 13109/92	01-10-1992
		AU B2 653210	22-09-1994
		CA AA 2063883	26-09-1992
		CS A3 9200887	14-10-1992
		CY A 2032	20-02-1998
		CZ B6 284756	17-02-1999
		DE C0 59202649	03-08-1995
		DK T3 505966	30-10-1995
		EP B1 505966	28-06-1995
		ES T3 2076592	01-11-1995
		FI A0 921248	23-03-1992
		FI A 921248	26-09-1992
		FI B 99084	30-06-1997
		FI C 99084	10-10-1997
		HR A1 940838	30-06-1997
		IE B 67555	17-04-1996
		IL A0 101346	15-11-1992
		JP A2 5070363	23-03-1993
		NO A0 921147	24-03-1992
		NO A 921147	28-09-1992
		NO B1 302856	04-05-1998
		NZ A 242073	26-08-1993
		ZA A 9202130	25-11-1992
US A 4835139	30-05-1989	CH A 661206	15-07-1987
US A 5540937	30-07-1996	AU A1 42022/93	10-02-1994
		AU B2 675788	20-02-1997
		CA AA 2100925	28-01-1994
		EP A1 585151	02-03-1994
		FR A1 2693905	28-01-1994
		FR B1 2693905	02-09-1994
		JP A2 6087758	29-03-1994
		NZ A 248207	27-02-1996
US A 5192741	09-03-1993	AT A 2234/88	15-06-1993
		AT B 397035	25-01-1994
		AU A1 22326/88	23-03-1989
		AU B2 611944	27-06-1991
		BE AF 1001685	06-02-1990
		CA A1 1326438	25-01-1994
		CH A 675968	30-11-1990
		DE A1 3822459	30-03-1989
		DE C2 3822459	07-07-1994
		DK A0 5189/88	16-09-1988
		DK A 5189/88	22-03-1989
		ES AF 2009346	16-09-1989
		FI A0 884297	19-09-1988
		FI A 884297	22-03-1989
		FI B 96919	14-06-1996
		FI C 96919	25-09-1996
		FR A1 2620621	24-03-1989
		FR B1 2620621	19-02-1993
		GB A0 8722134	28-10-1987
		GB A1 2209937	01-06-1989
		GB B2 2209937	03-07-1991
		GR A 881100619	22-06-1989
		GR B 1002244	22-04-1996
		IE B 60608	27-07-1994
		IL A0 87790	31-03-1989
		IL A1 87790	25-05-1992
		IT A0 8805213	20-09-1988
		IT A 1225148	02-11-1990
		JP A2 1121222	12-05-1989
		JP B4 7013023	15-02-1995
		LU A 87340	06-04-1989
		NL A 8802323	17-04-1989
		NO A0 884154	19-09-1988
		NO A 884154	22-03-1989
		NO B 178604	22-01-1996
		NO C 178604	02-05-1996
		PT A 88557	01-10-1988
		PT B 88557	30-11-1992
		SE A0 8803321	20-09-1988
		SE A 8803321	22-03-1989
		SE C2 503406	10-06-1996
		US A 5776885	07-07-1998
		ZA A 8806827	30-05-1989